


KEIM Restauro Grund Deep fill stone restoration mortar



1. Product description

Keim Restauro Grund is a mineral dry bagged pre mixed restoration mortar with hydraulic binders used for stone repair.

2. Field of application

The Keim Restauro system consists of natural stone replacement materials for reproducing the colour and texture of the original stone. Keim Restauro Grund can be used to restore stone surfaces as part of the Restauro Stone Restoration system.

Only suitable for depth of repairs in excess of 10-15mm.

3. Product properties

Easy to apply
Long lasting

Material characteristics

Bulk density: approx. 1.34g/cm³
Water consumption: approx. 0.14l/kg
Working time: max 45min
Setting time: approx 4 hr
Compressive strength: approx. 29N/mm²
Bending tensile strength: approx. 8N/mm²

Colour shades

Grey

4. Application instructions

Substrate preparation

Remove loose material and old coats mechanically or with a water pressure jet. All loose and friable material should be cut back to a sound level.

Application

Having cut the stone back to a sound base, Keim Restauro Grund, mixed with clean cold water to a moist earth consistency, should be applied to the level of approximately 5mm below the finished surface. Apply to pre-wetted surfaces in one or more layers from 10mm to 50mm maximum. Keim Restauro Grund is only suitable if the depth is in excess of 10 to 15mm.

Finishing

Once the base mortar has set, roughen the surface and allow at least one day to elapse before further finishing operations and application of Keim Restauro Top.

Application conditions

Ambient and substrate temperature above 5°C and below 30°C. Do not apply in direct sunlight or onto sun-heated surfaces, nor if it is raining or if there is an immediate likelihood of rain.

Consumption

Approximately 10kg/m² for 5mm thick repair. (Determine actual consumption by tests on trial areas.)

Consumption rates are offered for guideline purposes only and are quoted for smooth rendered surfaces. Actual rates are the responsibility of the applicator. Project specifications should be referred to for specific rates.

Cleaning of tools

Clean immediately after use with water

5. Packaging

30kg sacks



6. Storage

The product has a shelf life of 6 months, if stored in a dry, cool and frost free place.

7. Disposal

EC Waste Code No. 17 01 01

Any residues must be emptied out of sacks before recycling. Solidify any residual material with water and, after consulting the relevant authorities, dispose of in a building material landfill site.

8. Safety instructions

Cover surfaces which are not to be painted, in particular glass, natural stone, ceramics etc. Protect the eyes and skin from splashes. Keep out of reach of children.

Refer to COSHH data sheet.

The stated values and properties are the result of extensive development work and practical experience. Our recommendations for application, whether given verbally or in writing, are intended to provide assistance in the selection of our products and do not establish a contractual relationship. In particular, they do not release those purchasing and applying our products from the duty of establishing for themselves, with due care, the suitability of our products for the intended application. Standard building industry practices must be complied with. We retain the right to make modifications to improve the products or their application. This edition supersedes all earlier editions.

